



Technical Specifications

SATIN GLACIER 60# Text				
90 gsm				
Characteristics	Standards	Values	Units	Tolerances
Grammage	ISO 536	90.0	g/m ²	± 5
Thickness	ISO 534	100	microns	± 7
Bulk	ISO 534	1.11		
Stiffness Lorentzen	ISO 2493	(angle de 15°)		
Grain Direction		0.70	mNm	*
Cross Grain		0.35	mNm	*
Smoothness Bekk	ISO 5627			
Felt Side		55	s	*
Moisture	ISO 287	6.5	%	± 0.5
Opacity	ISO 2471			
Dry		89.0	%	*
Wet		78.0	%	*
Tensile Strength	ISO 1924-2			
Seconds Grain Direction		75.0	N/15mm	*
% Wet Strength Treatment	ISO3781	11.0	%	*
Cobb (60 sec.)	ISO 535	20.0	g/m ²	*
Whiteness	ISO 11476	138		*
Color	CIELAB 76	Delta E		< 1.2